

SPUNLACE CLOTH 45GSM



NON-WOVEN TYPE	APERTURED SPUNLACE	SPECIFICATION LIMITS
Composition:	Average	VIS 40% PET 60%
Width:	mm	-3 / +5mm
Weight (gr/m ²):	Average	39.60 – 50.40
Thickness:	Average	0.37 – 0.46
Absorption capacity:	g/5g	8 (min) – 10 (target)
Absorption rate:	seconds	5 (max) – 2 (target)
Tensile strength		
Dry (N) MD:	N/50 mm	35 (min) - 45 (target)
Dry (N) MD:	N/50 mm	12.5 (min) - 15 (target)
Wet (N) MD:	N/50 mm	25 (min) - 35 (target)
Wet (N) MD:	N/50 mm	10 (min) - 12.5 (target)
Elongation MD:	%	<60% / 40 (target)
Elongation CD:	%	<120% / 90 (target)
Mesh:		18
Print:		Wave
Colours:	Blue, Green, Red, Yellow, White	