

SPUNLACE JUMBO ROLL 45GSM



NON-WOVEN TYPE	APERTURED SPUNLACE	SPECIFICATION LIMITS
Composition:	Average	VIS 40% PET 70%
Width:	mm	-3 / +5mm
Weight (gr/m ²):	Average	41.0 – 51.0
Thickness (μ m):	4 ply	1500 - 1800
Absorption capacity:	%	>380
Absorption rate:	seconds	< 3.5
Tensile strength		
Dry (N):	MD	>50 / 20 - 80%
Dry (N):	CD	>23 / 40 – 100%
Wet (N):	MD	>100 / N/A
Wet (N):	CD	>20 / N/A
Colours:	Blue, Green, Red, Yellow, White	