

SPUNLACE CLOTH 70GSM



NON-WOVEN TYPE	APERTURED SPUNLACE	SPECIFICATION LIMITS
Composition:	Average	PET 100%
Width:	mm	-3 / +5mm
Weight (gr/m ²):	Average	61.60 – 78.4
Thickness (mm):	Average	.600 – 0.80
Absorption capacity:	g/ 5g	8 (min) – 10 (target)
Absorption rate:	second	5 (max) – 2 (target)
Tensile strength		
Dry (N) MD:	N/50mm	0 (min) – 120 (target)
Dry (N) CD:	N/50mm	45 (min) – 55 (target)
Wet (N) MD:	N/50mm	75 (min) – 100 (target)
Wet (N) CD:	N/50mm	40 (min) – 50 (target)
Elongation MD:	%	<60% / 40 (target)
Elongation CD:	%	<100% / 80 (target)
Size:	30cm x 50cm	
Quantity per pack:	50	
Mesh:		10
Colours:	Blue, Green, Red, Yellow, White	